

Douglas-Fir

{*Pseudotsuga menziesii*}



Douglas-Fir is one of the world's best-known timber species. In British Columbia (B.C.) there are two varieties: coastal and interior. Coastal Douglas-Fir occurs along the Southern mainland coast and across Vancouver Island, while the interior variety is found throughout Southern and Central B.C. At maturity, this large tree can reach a height of 85 metres on the coast, and 42 metres in the interior. Douglas-Fir is commonly used for building and construction purposes due to its extraordinary strength-to-weight ratio and availability in large dimensions.

COMMON USES

Douglas-Fir is seen as a first-class wood for a wide variety of products including furniture, general millwork, flooring, cabinets, veneer, vats, ship/boat construction, transmission poles, and marine pilings. Douglas-Fir is one of the finest timbers for heavy structural purposes, including laminated arches and roof trusses. Structurally it's used in the form of lumber, timbers, piles, and plywood.

WORKING PROPERTIES

Douglas-Fir has excellent strength properties and is well known for its workability. The wood dries rapidly with small dimensional movement and little tendency to check. It is relatively easy to work, with good machining qualities: it turns, planes and shapes well. The wood glues easily, has good nail and screw holding ability and produces a high-quality finish.

COASTAL VS. INTERIOR

The timber from the coastal region is generally lighter in colour, and more uniform in texture compared to timber grown in the interior. One of the main differences is that interior Douglas-Fir is less permeable to preservative treatments. Besides the mentioned properties, these two varieties have the same wood properties.



PHYSICAL PROPERTIES

STIFFNESS/ MOE (MPa)	Air Dry	13600
STRENGTH/MOR (MPa)	Air Dry	88.6
DENSITY (kg/m ³)	Air Dry	487
COMPRESSION PARALLEL (MPa)	Air Dry	50.1
SHEAR (MPa)	Air Dry	9.53
SHRINKAGE (air dried - 12%)	Tangential / Radial ratio	1.5



WORKING PROPERTIES

	PROCESS	PERFORMANCE	COMMENTS
MACHINING	Planing	Good	Good surface quality
	Shaping	Excellent	
	Sanding	Good	Very good sanding properties
FASTENING	Screwing	Excellent	Very good holding. Excellent resistance to splitting
	Nail Retention	Good	
	Gluing	Good	Bonds well with a fairly wide range of adhesives under a moderately wide range of bonding conditions.
FINISHING	Staining	Excellent	Good results with light stain or clear finish followed by nitrocellulose alkyd clear sealer and finish.
	Painting	Good	
DRYING	Ease of Drying	Good	A relatively easy wood to dry with little trouble occurring from checking, warping, and splitting. Lower grades require more care.
DURABILITY	Natural Decay Resistance	Fair	Should not be used in applications with prolonged ground contact without treatment.
	Treatability	Fair	Can be improved by incising



For more information on the availability of Douglas-Fir, please contact
info@canadianwood.in
 +91 22 4922 1600



TRY CANADIAN WOOD

www.canadianwood.in



canadianwoodindia



canadianwoodindia



canadian-wood